



# CASHMERE™

## INTERIOR LATEX MEDIUM LUSTRE D18 SERIES

CHARACTERISTICS	SPECIFICATIONS	SURFACE PREPARATION												
<p><b>Cashmere Interior Latex Medium Lustre</b> was developed primarily for the residential repaint contractor. This product provides the residential repaint contractor with a very silky and easy to apply product. The results are a high hiding enamel with a unique, smooth, low-stipple finish.</p> <p><b>Color:</b> Most ColorAnswers colors</p> <p><b>Coverage:</b> 350 - 400 sq ft/gal @ 4 mils wet; 1.5 mils dry</p> <p><b>Drying Time, @ 77°F, 50% RH:</b> temperature and humidity dependent</p> <p>Touch: 1 hour</p> <p>Recoat: 4 hours</p> <p><b>Flash Point:</b> N/A</p> <p><b>Finish:</b></p> <p><b>Sheen @ 85°</b> 85 - 95 units</p> <p><b>Gloss @ 60°</b> 50-60 units</p> <p><b>Tinting with Blend-A-Color:</b></p> <table border="1"> <thead> <tr> <th>Base</th> <th>oz/gal</th> <th>Strength</th> </tr> </thead> <tbody> <tr> <td>Luminous White</td> <td>0-5</td> <td>125%</td> </tr> <tr> <td>Extra White</td> <td>0-6</td> <td>125%</td> </tr> <tr> <td>Deep Base</td> <td>4-12</td> <td>100%</td> </tr> </tbody> </table> <p><b>Vehicle Type:</b> Vinyl Acrylic <b>D18W51</b></p> <p><b>VOC:</b> 73 g/L; 0.61lb/gal</p> <p><b>Volume Solids:</b> 36 ± 2%</p> <p><b>Weight Solids:</b> 46 ± 2%</p> <p><b>Weight per Gallon:</b> 10.0 lb</p>	Base	oz/gal	Strength	Luminous White	0-5	125%	Extra White	0-6	125%	Deep Base	4-12	100%	<p><b>Aluminum</b> 2 cts. Cashmere Medium Lustre</p> <p><b>Galvanized Steel</b> 1 ct. All Surface Enamel Latex Primer 2 cts. Cashmere Medium Lustre</p> <p><b>Block</b> 1 ct. Loxon Block Surfacer 2 cts. Cashmere Medium Lustre</p> <p><b>Drywall</b> 1 ct. PrepRite Classic Primer 2 cts. Cashmere Medium Lustre</p> <p><b>Plaster</b> 1 ct. PrepRite Wall and Wood Primer 2 cts. Cashmere Medium Lustre</p> <p><b>Masonry</b> 1 ct. PrepRite Masonry Primer 2 cts. Cashmere Medium Lustre</p> <p><b>Steel</b> 1 ct. All Surface Enamel Primer 2 cts. Cashmere Medium Lustre</p> <p><b>Wood, Composition Board</b> 1 ct. PrepRite Wall and Wood Primer 2 cts. Cashmere Medium Lustre</p>	<p>Warning! Removing or disturbing old paint from interior or exterior surfaces by sanding, scraping, abrading or other means may produce dust, debris or fumes that contain lead. Exposure to lead dust, debris or fumes may cause brain damage or other adverse health effects, especially in children and pregnant women. Structures built before 1978 should be tested by a licensed inspector prior to removing or disturbing old paint. For more information, call the National Lead Information Center at 1-800-424-LEAD (in U. S.) or contact your local health authority.</p> <p>Remove all surface contamination by washing with ProClean Professional™ Prep Wash Concentrated Cleaner or other appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with PrepRite ProBlock Primer Sealer.</p> <p><b>Aluminum and Galvanized Steel</b> Wash with a ProClean Professional Prep Wash Concentrated Cleaner to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, steel wool, or other abrading method.</p> <p><b>Drywall</b> Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.</p> <p><b>Masonry, Concrete, Cement, Block</b> All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite Masonry Primer.</p>
Base	oz/gal	Strength												
Luminous White	0-5	125%												
Extra White	0-6	125%												
Deep Base	4-12	100%												

101.62



# CASHMERE™

## INTERIOR LATEX MEDIUM LUSTRE D18 SERIES

SURFACE PREPARATION	APPLICATION	CAUTIONS
<p><b>Plaster</b> Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.</p> <p><b>Steel</b> Remove rust and mill scale using sandpaper, steel wool, or other abrading method. Prime bare steel the same day as cleaned.</p> <p><b>Wood</b> Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.</p> <p><b>Mildew</b> Remove before painting by washing with ProClean Professional™ Mildew Eliminator or a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. <b>DO NOT ADD DETERGENTS OR AMMONIA TO THE BLEACH/WATER SOLUTION.</b></p> <p><b>Caulking</b> Fill gaps between walls, ceilings, crown moldings, and other trim with Pro Select® Premium Siliconized Acrylic Latex Caulk 1100A after priming the surface.</p>	<p>Apply at temperatures above 50°F. No reduction needed.</p> <p><b>Brush</b> Use a nylon/polyester brush.</p> <p><b>Roller</b> Use a 3/8" - 3/4" nap synthetic cover.</p> <p><b>Spray—Airless</b> Pressure.....2000 psi Tip ..... .017"-.021"</p> <p><b>CLEANUP INFORMATION</b></p> <p>Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.</p> <p><b>MAINTENANCE</b></p> <p>To assure maximum washability and durability, wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water, or use EverClean™ All Surface Cleaner or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.</p>	<p>For interior use only. Protect from freezing. Non-photochemically reactive.</p> <p><b>CAUTION</b> Contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. <b>FIRST AID:</b> In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, get medical attention immediately. <b>DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.</b> Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. <b>WARNING:</b> This product contains chemicals known to the State of California to cause cancer. <b>DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.</b> LCE 10/4/2001</p> <p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.</p>