



101.31

CLASSIC 99®

INTERIOR LATEX SEMI-GLOSS A26 SERIES

<u>CHARACTERISTICS</u>	<u>SPECIFICATIONS</u>	<u>SURFACE PREPARATION</u>												
<p>Classic 99 Interior Latex Semi-Gloss is for use on walls, and trim of primed plaster, wallboard, wood, masonry, and primed metal. Classic 99 provides one coat hiding over many colors on smooth surfaces and will provide a durable, scrubbable, and washable finish.</p> <p>Color: Most colors</p> <p>Coverage: 350 - 400 sq ft/gal @ 4 mils wet; 1.5 mils dry</p> <p>Drying Time, @ 77°F, 50% RH: temperature and humidity dependent Touch: 1 hour Recoat: 4 hours</p> <p>Flash Point: N/A</p> <p>Finish: 25-35 units @ 60°</p> <p>Tinting with Blend-A-Color:</p> <table border="1"> <thead> <tr> <th>Base</th> <th>oz/gal</th> <th>Strength</th> </tr> </thead> <tbody> <tr> <td>Luminous White</td> <td>0-5</td> <td>100%</td> </tr> <tr> <td>Extra White</td> <td>0-5</td> <td>100%</td> </tr> <tr> <td>Deep Base</td> <td>4-12</td> <td>100%</td> </tr> </tbody> </table> <p>Vehicle Type: Vinyl Acrylic A26W51</p> <p>VOC (less exempt solvents): 85 g/L; 0.71 lb/gal</p> <p>Volume Solids: 38 ± 2%</p> <p>Weight Solids: 46 ± 2%</p> <p>Weight per Gallon: 9.9 lb</p> <p>Provides performance which is comparable to the products that are formulated in accordance with federal specification: AA 2246 Class 3</p>	Base	oz/gal	Strength	Luminous White	0-5	100%	Extra White	0-5	100%	Deep Base	4-12	100%	<p>Aluminum 2 cts. Classic 99 Interior Latex Semi-Gloss</p> <p>Galvanized Steel 1 ct. All Surface Enamel Latex Primer 2 cts. Classic 99 Interior Latex Semi-Gloss</p> <p>Block 1 ct. Loxon Block Surfacers 2 cts. Classic 99 Interior Latex Semi-Gloss</p> <p>Drywall 1 ct. PrepRite Classic Latex Primer 2 cts. Classic 99 Interior Latex Semi-Gloss</p> <p>Plaster 1 ct. PrepRite Classic Latex Primer 2 cts. Classic 99 Interior Latex Semi-Gloss</p> <p>Masonry 1 ct. PrepRite Masonry Primer 2 cts. Classic 99 Interior Latex Semi-Gloss</p> <p>Steel 1 ct. All Surface Enamel Primer 2 cts. Classic 99 Interior Latex Semi-Gloss</p> <p>Wood, Composition Board 1 ct. PrepRite Classic Latex Primer 2 cts. Classic 99 Interior Latex Semi-Gloss</p>	<p>WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p>Remove all surface contamination by washing with ProClean Professional™ Prep Wash Concentrated Cleaner or other appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with PrepRite ProBlock Primer Sealer.</p> <p>Aluminum and Galvanized Steel Wash with a ProClean Professional Prep Wash Concentrated Cleaner to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, steel wool, or other abrading method.</p> <p>Drywall Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.</p>
Base	oz/gal	Strength												
Luminous White	0-5	100%												
Extra White	0-5	100%												
Deep Base	4-12	100%												

101.31



CLASSIC 99®

INTERIOR LATEX SEMI-GLOSS A26 SERIES

SURFACE PREPARATION

Masonry, Concrete, Cement, Block

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite Masonry Primer.

Plaster

Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

Steel

Rust and mill scale must be removed using sandpaper or other abrading method. Bare steel must be primed the same day as cleaned.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Mildew

Remove before painting by washing with ProClean Mildew Eliminator or a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Caulking

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with Pro Select® Premium Siliconized Acrylic Latex Caulk 1100A after priming the surface.

APPLICATION

Apply at temperatures above 50°F.

No reduction needed.

Brush

Use a nylon/polyester brush.

Roller

Use a 1/4" - 3/4" nap synthetic cover.

Spray—Airless

Pressure 2000 psi

Tip017"-.021"

CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

MAINTENANCE

To assure maximum washability and durability, wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water, or use EverClean™ All Surface Cleaner or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.

CAUTIONS

For interior use only.

Protect from freezing.

Non-photochemically reactive.

LABEL CAUTIONS

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, Call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.
LCE 10/22/01 A26W51 04 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.