



101.10

# EVERCLEAN®

## INTERIOR LATEX SATIN A97 SERIES

### CHARACTERISTICS

**EverClean Interior Latex Satin** is a specially formulated paint providing the washability and durability usually found in glossy enamel finishes. It allows most household stains to be removed without the need for scrubbing.

**Color:** Most colors

**Coverage:** 350 - 400 sq. ft./gal.  
@ 4 mils wet; 1.5 mils dry

**Drying Time, @ 77°F, 50% RH:**  
temperature and humidity dependent

Touch: 1 hour

Recoat: 4 hours

**Flash Point:** N/A

**Finish:** 10-20 units @ 85°

**Tinting with Blend-A-Color:**

<b>Base</b>	<b>oz/gal</b>	<b>Strength</b>
-------------	---------------	-----------------

<b>Base</b>	<b>oz/gal</b>	<b>Strength</b>
-------------	---------------	-----------------

Luminous Base	0-5	Special
---------------	-----	---------

Extra White	0-5	Special
-------------	-----	---------

Deep Base	4-12	Special
-----------	------	---------

**Vehicle Type:** Acrylic

**A97W51**

**VOC (less exempt solvents):**

187 g/L; 1.56 lb/gal

**Volume Solids:** 38 ± 2%

**Weight Solids:** 51 ± 2%

**Weight per Gallon:** 10.7 lb

Meets the performance requirements, not necessarily composition, of Federal Specification:

AA 2246 Class 2

#### **Mildew Resistant**

This product contains agents which inhibit the growth of mildew on the surface of this paint film

### SPECIFICATIONS

#### **Block**

1 ct. PrepRite Block Filler

2 cts. EverClean Interior Latex Satin

#### **Drywall**

1 ct. PrepRite Classic Primer

2 cts. EverClean Interior Latex Satin

#### **Plaster**

1 ct. PrepRite Classic Primer

2 cts. EverClean Interior Latex Satin

#### **Masonry**

1 ct. PrepRite Masonry Primer

2 cts. EverClean Interior Latex Satin

#### **Wood, Composition Board**

1 ct. PrepRite Classic Latex Primer

2 cts. EverClean Interior Latex Satin

### SURFACE PREPARATION

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Remove all surface contamination by washing with ProClean Professional™ Prep Wash Concentrated Cleaner or other appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with PrepRite ProBlock Primer Sealer.

#### **Drywall**

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

#### **Masonry, Concrete, Cement, Block**

All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite Masonry Primer.

#### **WASHABILITY TEST —ASTM D3450-90**

“Coating will retain, on average, greater than 80.0% reflectance after standardized soilant has been washed with either an abrasive or nonabrasive cleanser for 100 cycles when tested in accordance with ASTM D3450-90”

101.10



# EVERCLEAN®

## INTERIOR LATEX SATIN A97 SERIES

### SURFACE PREPARATION

#### Plaster

Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

#### Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

#### Mildew

Remove before painting by washing with ProClean Mildew Eliminator or a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

#### Caulking

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with Pro Select Premium Sili-conized Acrylic Latex Caulk 1100A after priming the surface.

### APPLICATION

Apply at temperatures above 50°F.

No reduction needed.

#### Brush

Use a nylon/polyester brush.

#### Roller

Use a 3/8" - 1/2" nap Soft Woven roller cover only.

#### Spray—Airless

Pressure ..... 2000 psi

Tip ..... .015"-.019"

For touching-up, reduce the product by one pint per gallon.

### CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. Flush spray equipment after cleaning with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

### CARE AND WASHING INSTRUCTIONS

To assure maximum washability and durability, wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water, or use EverClean All Surface Cleaner or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.

### CAUTIONS

For interior use only.

Protect from freezing.

Non-photochemically reactive.

#### LABEL CAUTIONS

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, Call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

LCE 10/23/01 A97W51 04 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.